

SUITABILITY OF CAST ALLOYS FOR ANODISING

Alloy	Anodising Against Corrosion	Anodising for Dyeing	Bright Anodising
LM0	E	E	E
LM2	F	U	U
LM4	G	F(1)	U
LM5	E	E	G
LM6	F	U	U
LM9	F	U	U
LM12	F	F	U
LM13	F	U	U
LM16	G	F(1)	U
LM20	G	F(1)	U
LM21	F	U	U
LM22	G	F	U
LM24	F	F(1)	U
LM25	G	F(1)	U
LM26	F	U	U
LM27	G	F(1)	U
LM28	U	U	U
LM29	U	U	U
LM30	U	U	U
LM31	E	E	F
BS2L99	G	F(1)	U
BSL119	G	G	U
BSL154	G	G	U
BSL155	G	G	U
BSL169	G	F(1)	U
BSL173	G	F(1)	U
BSL174	G	F(1)	U
DTD716B	G	F(1)	U
DTD722B	G	F(1)	U
DTD727B	G	F(1)	U
DTD735B	G	F(1)	U
DTD5008B	E	E	F
DTD5018A	E	F(2)	U

E-Excellent G-Good F-Fair P-Poor U-Unsuitable
 1. Only suitable for dark colours
 2. Anodizing conditions must be carefully controlled for good results